

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : G02B 1/04, C08J 7/18	A1	(11) International Publication Number: WO 99/15917 (43) International Publication Date: 1 April 1999 (01.04.99)
(21) International Application Number: PCT/EP98/06005 (22) International Filing Date: 21 September 1998 (21.09.98) (30) Priority Data: 60/059,800 23 September 1997 (23.09.97) US (71) Applicant (for all designated States except AT): NOVARTIS AG [CH/CH]; Schwarzwaldallee 215, CH-4058 Basel (CH). (71) Applicant (for AT only): NOVARTIS-ERFINDUNGEN VERWALTUNGSGESELLSCHAFT MBH [AT/AT]; Brunner Strasse 59, A-1235 Vienna (AT). (72) Inventors: BARON, Richard, Carlton; 115 Kiltirman Court, Alpharetta, GA 30201 (US). LIU, Qin; 4411 Northwest Snowbrush Drive, Corvallis, OR 97330 (US). (74) Agent: BECKER, Konrad; Novartis AG, Patent- und Markenabteilung, Lichtstrasse 35, CH-4002 Basel (CH).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: METHOD FOR HYDROGEL SURFACE TREATMENT AND ARTICLE FORMED THEREFROM (57) Abstract <p>A method of modifying the surface characteristics of a polymeric hydrogel, and a polymer article formed therefrom, without causing substantial swelling or distortion of the hydrogel. A preferred method includes photoinitiating of the surface of the article with a benzophenone and grafting a macromer having a number-average molecular weight greater than 1000 in the presence of UV irradiation. The preferred article is a siloxane-containing hydrogel, especially a soft contact lens.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Method for Hydrogel Surface Treatment and Article Formed Therefrom

This invention relates broadly to surface modification of polymeric hydrogels. More particularly, the invention relates to the treatment of ophthalmic lenses, especially siloxane-containing hydrogel contact lenses.

Generally speaking, methods of treating polymer surfaces include (1) corona discharge, (2) surface degradation or oxidation by oxidizing agents such as chromic acid, (3) plasma treatment and/or plasma polymerization, (4) graft polymerization, and (5) coating.

US 4,892,402, for example, discloses a method for making hard contact lenses more hydrophilic. The method involves contacting a hard lens with a treatment solution containing a hydrophilic monomer, at least one photosensitizer selected from aromatic ketones or quinones, and a solvent, and then irradiating the lens with ultraviolet light. Thus, the disclosed method is a solvent-based polymerization. Benzophenone is an example of a suitable photosensitizer.

While there exist numerous methods of surface treating polymeric articles, there remain problems with the surface treatment of hydrogel materials, especially those suited as ophthalmic lenses. One problem with many surface grafting techniques is that monomer in the treatment solution may penetrate the hydrogel's polymer matrix, and subsequently bind to the polymer below the article's surface. If substantial monomer penetration occurs, the treated polymeric article may swell and distort from the original shape. Even slight distortion can produce substantial optical distortions in an ophthalmic lens. Thus, there remains a need for a method of surface treating hydrogel materials without substantially modifying the shape of the hydrogel.

An object of the invention is to modify the surface properties of a polymeric hydrogel, without substantially modifying the shape of the hydrogel.

A further object of the invention is to increase the hydrophilicity of the surface of a polymeric hydrogel, without substantially modifying the shape of the hydrogel.

- 2 -

Another object of the invention is to increase the hydrophilicity of the surface of a hydrophilic ophthalmic lens, without substantially impairing the optical properties of the lens.

The present invention relates to a method of treating the surface of a polymeric article, which includes the following steps:

- (a) immersing a polymeric article in a first solution including a benzophenone and at least one solvent for a predetermined time period;
- (b) removing said article from said first solution;
- (c) evaporating at least a portion of said solvent from said article;
- (d) placing said article in a second solution containing at least one macromer; and
- (e) applying radiation to said article for a period sufficient to cause at least a portion of said macromers to bond to the surface of said article,

wherein said macromer has a size sufficiently large such that no substantial amount of macromer penetrates said article and causes substantial distortion of said article.

Another embodiment is a polymeric hydrogel article including a core bulk material and a surface coating. The surface coating is formed by graft polymerization with surface photoinitiation in the presence of a benzophenone. The grafted groups are formed from one or more macromers having a size sufficiently large such that no substantial amount of macromer penetrates said lens causing substantial distortion of said lens. The preferred polymeric article is a soft contact lens including a bulk material which is a silicone-containing hydrogel.

The following terms are defined at the outset in order to facilitate a clear understanding of the present invention. Certain terms are defined subsequently in the text because of the limited use herein.

The term "copolymer", as used herein, means polymers formed from two or more monomers or macromers. Thus, copolymer includes terpolymers and the like.

The term "macromer" as used herein refers to a species having at least one unsaturated bond and having at least two repeating monomer units.

The term "hydrogel", as used herein, refers to a polymeric material which contains at least about 10 weight percent water when fully saturated.

The present invention is related to a method of modifying the surface characteristics of a polymeric article, e.g. a polymeric hydrogel. The preferred polymeric articles useful in accordance with the present invention are silicone-containing hydrogel materials. A more preferred subclass of articles which may be treated in accordance with the present invention are ophthalmic lenses, including without limitation thereto, contact lenses, intraocular lenses (i.e., implants), and lenses designed for delivery of pharmaceuticals or other agents to the ocular environment. Contact lenses are the most preferred treatment article, in particular soft contact lenses.

The term "Photosensitizer", as used herein include, without limitation thereto, benzophenone, thioxanethen-9-one, 2-acetonaphthone, mixtures thereof and the like.

The term "benzophenone", as used herein, means benzophenone and derivatives thereof which are suited to initiating surface bonding to a contact lens polymer in the presence of applied light, i.e., derivatives suited to photoinitiation of surface polymerization. Thus, "benzophenone" includes, without limitation thereto, 2-amino benzophenone; 2-amino-5-chloro benzophenone; 2-amino-4'-methyl benzophenone; 2-amino-5-methyl benzophenone; 2-amino-5-nitro benzophenone; 3-amino benzophenone; 3-amino-4-methyl benzophenone; 3-amino-4'-methyl benzophenone; 4-amino benzophenone; 4-amino-3-methyl benzophenone; 4-amino-4'-methyl benzophenone. A more preferred group of benzophenones includes benzophenone; 4-fluorobenzophenone; 4-chlorobenzophenone; 4-benzoylbenzoic acid; 3,3'-4,4'-benzophenone tetracarboxylic dianhydride, Mischler's ketone, and mixtures thereof.

The first treatment solution is intended to functionalize the lens surface, i.e., to prepare the surface for facile grafting or bonding of macromeric species thereto. The solution may include about 0.1 to 10 millimoles/liter (mmol/L) benzophenone, about 10 to 50 weight percent solvent, and about 90 to 50 weight percent water, in which the water and solvent weight percentages are based on the water/solvent mixture. More preferably, the first solution includes about 0.5 to 5 weight percent benzophenone, about 20 to 40 weight percent solvent, and about 60 to 40 weight percent water. Suitable solvents for benzophenone include, without limitation thereto, short chain alcohols such as isopropanol,

ethanol, and the like. Preferably, the solvent is miscible with water, so that a homogeneous system is produced.

While the invention is not limited to theoretical explanations of operability, the following theory is offered to better enable the reader to understand the invention. It is believed that the benzophenone separates out of the solution at unduly low solvent levels. Thus, low solvent levels may create a heterogeneous system, and promote non-uniform surface functionalization. However, increasing solvent concentration may cause the lens to swell. The swelling is believed to increase the lens porosity. At excessively high solvent concentrations, the pores in the lens material are large enough to allow penetration of the macromer into the lens structure, thereby causing lens deformation and optical distortions. Thus, a proper surface treatment is achieved by maintaining the solvent concentration high enough to provide a homogeneous mixture (and uniform treatment), while maintaining the solvent concentration below the point at which unacceptable macromer penetration (and optical distortion) occurs.

The first solution may be exposed to the lens for a period of about 1 to 30 minutes, more preferably about 5 to 20 minutes, and most preferably about 8 to 12 minutes. Subsequent to contact with the first solution, the lens is removed from the first solution and evaporated under conditions which do not substantially damage the lens.

Evaporation of the solvent is preferred. Evaporation may be accomplished in a number of ways, including air drying and application of a limited amount of heat or air currents. The lens may be air dried for about 30 minutes to 3 hours, more preferably about 1 to 2 hours, depending on the temperature and relative humidity. Subsequent to air drying, the lenses may be placed in a nitrogen atmosphere. Then, a vacuum may be generated, preferably at a pressure of less than about 0.5 millibars. More preferably, the lenses are nitrogen and vacuum treated during two or more cycles.

The amount of water and/or solvent remaining in the lens depends on the specific treatment composition selected and the core polymer material chosen for treatment. It is preferable to remove the bulk of the solvent so that the photosensitizer remains on the surface of the article to be treated. Preferably, the solvent and water are substantially completely

evaporated, i.e., less than 50 weight percent solvent/water remains in the lens. More preferably, less than about 25 weight percent solvent/water remains in the lens.

Preferably subsequent to the evaporation step, the lens is contacted with a second solution including macromer. The second solution preferably includes about 1 to 50 weight percent macromer and about 99 to 50 weight percent water. More preferably, the second solution includes about 5 to 10 weight percent macromer and about 95 to 90 weight percent water.

After contacting the lens with the macromer-containing solution, grafting of the macromer to the lens surface is initiated by applying ultraviolet light in an amount and for a time sufficient to cause a substantial amount of the macromer to bond to the lens surface. The UV light may be applied at an intensity of about 25 to about 100 milliwatts per square centimeter (mW/cm^2) for a period of about one minute to one hour. More preferably, the UV light is applied at an intensity of about 50 to about 60 mW/cm^2 for a period of about 5 to 20 minutes.

Subsequent to photoinitiation of the macromer-bonding reaction, the lens may be subjected to an optional step of extraction to remove any undesirable remaining solvent. For example, the lens may be rinsed with a solution of deionized water, followed by a solution of about 10 to 30 weight percent isopropanol with about 90 to 70 weight percent water.

A wide variety of hydrophilic macromers are useful in the present invention, including without limitation thereto, polyalkylene oxides such as polyethylene oxide; polydimethylacrylamides; polyvinyl alcohols; poly(acrylates); poly(methacrylates) such as poly(2-hydroxyethyl methacrylate); poly(N-vinylpyrrolidone); poly(acrylamides) such as poly(N,N-dimethylacrylamide); derivatives, copolymers, mixtures thereof, and the like. A more preferred group of hydrophilic macromers includes polyethylene oxides, polyvinyl alcohols, and polyacrylamides, especially poly(N,N-dimethylacrylamide). Furthermore, it may be possible to apply a mixture of functionalized macromers with polymers.

However, the macromers useful in accordance with the present invention must have a size sufficient to prevent the macromer from substantially penetrating the polymer network of the lens. If the polymer network is penetrated, the lens may swell and become distorted. Minor amounts of swelling can cause intolerable amounts of deviation in the intended overall or

localized optical power of the lens, thereby distorting the vision of the ultimate consumer. Also, a poor fit to the consumer's eye can occur if the lens swells. Moreover, the unpredictability of the swelling can further complicate matters. Accordingly, the macromers useful in the present invention have a size sufficiently large such that no substantial amount of macromer penetrates the article to be treated (e.g., a contact lens) causing substantial distortion of the article.

With respect to optical lenses, the macromers preferably have a size sufficiently large to produce a contact lens having a final diameter which differs less than 10% with respect to the diameter of the untreated lens. More preferably, the lens diameter changes less than about 5%, even more preferably, less than about 2%.

One method of measuring the relative size of a macromer is molecular weight. The preferred molecular weight of the macromers is a number-average molecular weight greater than about 500. A more preferred number-average molecular weight is above about 1000.

The previous disclosure will enable one having ordinary skill in the art to practice the invention. Reference to the following examples is suggested.

EXAMPLE I

Hydrogel contact lenses are soaked in a first solution including about 3 mmol/L benzo-phenone in a 70/30 weight ratio water/isopropyl alcohol mixture. The lenses are air dried at room temperature for about 90 minutes. The lenses are placed in a nitrogen atmosphere in a chamber which is evacuated under 2 cycles vacuum in order to degas the lenses.

After degassing, the lenses are placed into molds containing a solution of polyvinylalcohol (PVA) macromer at a concentration of about 5 weight percent in water. The macromer has a number-average molecular weight of about 16,000 grams/mol.

The molds, which contain the lenses and macromer solution, are subjected to ultraviolet light at an intensity of about 5.8 to 6.0 mW/cm² for about 10 minutes, in order to bond the macromer to the lens surface.

After treatment, the lenses are removed from the molds and rinsed with deionized water, followed by a rinsing with a 20/80 volume ratio isopropanol/water solution. The lenses are autoclaved at a temperature of about 121°C for a period of about 30 minutes before measurements are taken.

COMPARATIVE EXAMPLE II

The treatment procedures described in Example I are followed substantially in this Example, with the exception being that the macromer is a polyoxyethylene having number-average molecular weight of about 1000.

CLAIMS

1. A method of treating the surface of a polymeric article, comprising the steps of:
 - (a) immersing a polymeric article in a first solution including a photosensitizer and at least one solvent for a predetermined time period;
 - (b) removing said article from said first solution;
 - (c) evaporating at least a portion of said solvent from said article;
 - (d) placing said article in a second solution containing at least one macromer; and
 - (e) applying radiation to said article for a period sufficient to cause at least a portion of said monomers or macromers to bond to the surface of said article,wherein said macromer has a size sufficiently large such that no substantial amount of macromer penetrates said article causing substantial distortion of said article.
2. A method of claim 1, wherein said photosensitizer is selected from the group consisting of benzophenone, thioxanethen-9-one, 2-acetonaphthone, mixtures thereof and the like.
3. A method of claim 2, wherein said photosensitizer is a benzophenone.
4. A method of claim 3, wherein said benzophenone is selected from the group consisting of benzophenone; 4-fluorobenzophenone; 4-chlorobenzophenone; 4-benzoylbenzoic acid; 3,3'-4,4'-benzophenone tetracarboxylic dianhydride, Mischler's ketone, and mixtures thereof.
5. A method of claim 1, wherein said macromer has a number-average molecular weight of at least 500.
6. A method of claim 4, wherein said macromer has a number-average molecular weight of at least 1000.
7. A method of claim 1, wherein said article is a hydrogel, having at least about 10 weight percent water when fully hydrated.
8. A method of claim 1, wherein said macromer is selected from the group consisting of polyalkylene oxides, polydimethyl acrylamides, mixtures thereof, and copolymers thereof.

9. A method of claim 10, wherein said macromer is a polyethylene oxide.
10. A method as recited in claim 1, wherein said macromer is a polyalkylene oxide having a number-average molecular weight greater than about 1000.
11. A method of claim 1, wherein said polymeric article is formed from a silicon-containing polymer.
12. A method of claim 18, wherein said silicon-containing polymer is a polydimethylsiloxane.
13. A method of claim 1, wherein said article is a contact lens.
14. A polymeric article having a surface with properties different from the bulk polymeric article material, said polymeric article comprising:
 - (a) a polymeric article bulk material selected from the group consisting of siloxane-containing polymers;
 - (b) a surface coating on said polymeric article bulk material, said surface coating including pendant groups formed by graft polymerization by surface photoinitiation with a benzophenone, said pendant groups being formed from one or more macromers having a size sufficiently large such that no substantial amount of macromer penetrates said lens causing substantial distortion of said article.
15. An article of claim 21, wherein said article is selected from the group consisting of contact lenses, intraocular lenses, implants, and ophthalmic agent delivery devices.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 98/06005

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 G02B1/04 C08J7/18

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 G02B C08J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 96 20919 A (CIBA GEIGY AG ;CHABRECEK PETER (CH); DIETLIKER KURT (CH); LOHMANN) 11 July 1996 see page 27, paragraph 2; claims 40-49 see page 31, paragraph 4; example F6 ---	1-15
X	WO 96 20796 A (CIBA GEIGY AG ;CHABRECEK PETER (CH); LOHMANN DIETER (CH)) 11 July 1996 see page 27, paragraph 2-4; claims ---	1-15
X	EP 0 632 329 A (CIBA GEIGY AG) 4 January 1995 see page 17, line 28 - page 19, line 12; claims; examples C6,D6 ---	1-15
	--- -/--	



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

18 February 1999

Date of mailing of the international search report

26/02/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Deraedt, G

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 98/06005

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 135 297 A (VALINT JR PAUL L) 4 August 1992 see claims ---	1-15
A	US 4 892 402 A (SAWAMOTO TAKEYUKI ET AL) 9 January 1990 cited in the application see claims -----	1-15

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 98/06005

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9620919 A	11-07-1996	AT 173742 T	15-12-1998
		AU 4251496 A	24-07-1996
		AU 692979 B	18-06-1998
		AU 4251596 A	24-07-1996
		AU 4251696 A	24-07-1996
		AU 700575 B	07-01-1999
		AU 4387396 A	24-07-1996
		BR 9510122 A	30-12-1997
		BR 9510177 A	23-12-1997
		CA 2208664 A	11-07-1996
		CA 2208967 A	11-07-1996
		CA 2208977 A	11-07-1996
		CA 2208996 A	11-07-1996
		WO 9620964 A	11-07-1996
		WO 9621167 A	11-07-1996
		WO 9620795 A	11-07-1996
		CN 1171798 A	28-01-1998
		CN 1173227 A	11-02-1998
		CN 1173148 A	11-02-1998
		CN 1174547 A	25-02-1998
		CZ 9702061 A	15-10-1997
		DE 59504366 D	07-01-1999
		EP 0800541 A	15-10-1997
		EP 0800657 A	15-10-1997
		EP 0793541 A	10-09-1997
		EP 0800511 A	15-10-1997
		FI 972611 A	18-06-1997
		FI 972698 A	25-08-1997
		FI 972737 A	27-08-1997
		FI 972738 A	30-06-1997
		HU 77423 A	28-04-1998
		JP 10512308 T	24-11-1998
		JP 10512000 T	17-11-1998
		JP 10512239 T	24-11-1998
		JP 10512856 T	08-12-1998
		NO 973018 A	19-08-1997
		NO 973019 A	26-08-1997
		NO 973020 A	26-08-1997
		NO 973021 A	01-09-1997
		NZ 297369 A	23-12-1998
		PL 321142 A	24-11-1997
		ZA 9511002 A	01-07-1996
WO 9620796 A	11-07-1996	AT 173742 T	15-12-1998
		AU 4251496 A	24-07-1996
		AU 692979 B	18-06-1998
		AU 4251596 A	24-07-1996
		AU 4251696 A	24-07-1996
		AU 698098 B	22-10-1998
		AU 4387496 A	24-07-1996
		BR 9510122 A	30-12-1997
		BR 9510292 A	11-11-1997
		BR 9510415 A	19-05-1998
		CA 2208710 A	11-07-1996
		CA 2208967 A	11-07-1996
		CA 2208977 A	11-07-1996
		CA 2208996 A	11-07-1996
		WO 9620964 A	11-07-1996

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 98/06005

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9620796 A		WO 9621167 A	11-07-1996
		WO 9620795 A	11-07-1996
		CN 1171798 A	28-01-1998
		CN 1173227 A	11-02-1998
		CN 1173148 A	11-02-1998
		CN 1174525 A	25-02-1998
		CZ 9702061 A	15-10-1997
		DE 59504366 D	07-01-1999
		EP 0800541 A	15-10-1997
		EP 0800657 A	15-10-1997
		EP 0793541 A	10-09-1997
		EP 0808222 A	26-11-1997
		FI 972611 A	18-06-1997
		FI 972699 A	22-08-1997
		FI 972737 A	27-08-1997
		FI 972738 A	30-06-1997
		HU 77423 A	28-04-1998
		JP 10512308 T	24-11-1998
		JP 10512000 T	17-11-1998
		JP 10512239 T	24-11-1998
		JP 10511600 T	10-11-1998
		NO 973018 A	19-08-1997
		NO 973019 A	26-08-1997
		NO 973020 A	26-08-1997
		NO 973022 A	25-08-1997
		NZ 297369 A	23-12-1998
		PL 321142 A	24-11-1997
		ZA 9511003 A	01-07-1996
EP 0632329 A	04-01-1995	AT 160888 T	15-12-1997
		AU 683256 B	06-11-1997
		AU 6603994 A	23-02-1995
		CA 2127200 A	03-01-1995
		CN 1102825 A	24-05-1995
		CZ 9401610 A	18-01-1995
		DE 59404708 D	15-01-1998
		DK 632329 T	04-05-1998
		ES 2109647 T	16-01-1998
		FI 943129 A	03-01-1995
		GR 3025768 T	31-03-1998
		HU 69305 A	28-09-1995
		JP 7089925 A	04-04-1995
		MX 9404973 A	31-01-1995
		NO 942495 A	03-01-1995
		NZ 260892 A	27-02-1996
		PL 304064 A	09-01-1995
		US 5527925 A	18-06-1996
		US 5612389 A	18-03-1997
		US 5612391 A	18-03-1997
		US 5621018 A	15-04-1997
		ZA 9404758 A	03-01-1995
US 5135297 A	04-08-1992	AT 163300 T	15-03-1998
		CA 2095044 A	28-05-1992
		CN 1061786 A	10-06-1992
		DE 69128940 D	26-03-1998
		DE 69128940 T	09-07-1998
		EP 0559820 A	15-09-1993

INTERNATIONAL SEARCH REPORT

information on patent family members

Inter. Appl. Application No

PCT/EP 98/06005

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5135297 A		ES 2113941 T	16-05-1998
		JP 6503118 T	07-04-1994
		WO 9209650 A	11-06-1992
US 4892402 A	09-01-1990	JP 2551580 B	06-11-1996
		JP 63271410 A	09-11-1988